

检测报告/Test Report

报告编号:
Report No.: A2210111285101001E

第 1 页 共 7 页
Page 1 of 7

委托单位: 青岛食安库食品安全科技有限公司
Applicant: Qingdao Shianku Food Safety Technology Co., Ltd.
地 址: 山东省青岛市高新区华贵路 819 号联东 U 谷 5 号楼 101 户
Address: Room 101, building 5, Liandong U Valley, 819 Huaguan Road, high tech Zone, Qingdao City, Shandong Province

样品信息/Report on the submitted sample said to be:

样品名称/Sample Name : 食安库 304 不锈钢板材/SHIANKU 304 stainless steel plate
CTI 样品编号/CTI Sample No. : CN08338001
材质/Material : 304 不锈钢/304 stainless steel
样品数量/Sample Quantity : 3 片/3 pcs
样品状态/Sample State : 固体/solid
样品接收日期/Sample Received Date : 2021/03/31
样品检测日期/Sample Tested Date : 2021/03/31~2021/04/12

检测部位描述 食安库 304 不锈钢板材 SHIANKU 304 stainless steel plate

/ Test Part Description:

检测项目/ Test Item(s): 请参见下页。/ Please refer to the following page(s).

检测结果/ Test Result(s): 请参见下页。/ Please refer to the following page(s).

检测结论/Test Conclusion: 经检验, 所检项目符合 GB 4806.9-2016《食品安全国家标准 食品接触用金属材料及制品》标准规定的技术要求。/Upon testing, the test item(s) of the submitted sample(s) comply with GB 4806.9-2016.



金 芷

审 核:
Reviewed by:

计会敏



批 准:
Approved by:

吴秀宏

日 期:
Date:

2021/04/13

吴秀宏 Alice
Technical director

报告编号: A2210111285101001E
Report No.:

第 2 页共 7 页
Page 2 of 7

检测结果:

Test Result(s):

序号 No.	检测项目 Test Item(s)	单位 Unit	检测结果 Test Result	检出限 DL	标准要求 Limit	结论 Conclusion	检测方法 Test Method
1	感官 Sense organ	/	接触食品的表面清洁, 镀层不开裂、剥落, 焊接部分光洁, 无气孔、裂缝、毛刺 The surface to be in contact with food was clean, the plating did not crack, peel, the welding part was smooth, no pores, cracks, burrs	/	接触食品的表面应清洁, 镀层不应开裂、剥落, 焊接部分应光洁, 无气孔、裂缝、毛刺 The surface to be in contact with food should be clean, the plating should not crack, peel, the welding part should be smooth, no pores, cracks, burrs	符合 Pass	GB 4806.9-2016

报告编号: A2210111285101001E
Report No.:

第 3 页共 7 页
Page 3 of 7

检测结果:

Test Result(s):

序号 No.	检测项目 Test Item(s)	单位 Unit	检测结果 Test Result	检出限 DL	标准要求 Limit	结论 Conclusion	检测方法 Test Method
2	浸泡液 Soaking solution	/	迁移试验 所得浸泡 液无异臭 The Immersion solutions obtained from migration test have no foreign smell	/	迁移试验 所得浸泡 液不应有 异臭 The Immersion solutions obtained from migration test should have no foreign smell	符合 Pass	GB 4806.9-2016
砷(As) Arsenic							
3	4%乙酸(体积分数), 煮沸 30min,室温放置 24h 4% acetic acid (v/v), boiled for 30min, leave at room temperature for 24h	mg/kg	未检出 N.D.	0.005	≤0.04	符合 Pass	GB 31604.49-2016 第二部分 第一法 The second part The first method
镉(Cd) Cadmium							
4	4%乙酸(体积分数), 煮沸 30min,室温放置 24h 4% acetic acid (v/v), boiled for 30min, leave at room temperature for 24h	mg/kg	未检出 N.D.	0.005	≤0.02	符合 Pass	GB 31604.49-2016 第二部分 第一法 The second part The first method

报告编号: A2210111285101001E
Report No.:

第 4 页共 7 页
Page 4 of 7

检测结果:

Test Result(s):

序号 No.	检测项目 Test Item(s)	单位 Unit	检测结果 Test Result	检出限 DL	标准要求 Limit	结论 Conclusion	检测方法 Test Method
铅(Pb) Lead							
5	4% 乙酸(体积分数), 煮沸 30min, 室温放置 24h 4% acetic acid (v/v), boiled for 30min, leave at room temperature for 24h	mg/kg	未检出 N.D.	0.005	≤ 0.05	符合 Pass	GB 31604.49-2016 第二部分 第一法 The second part The first method
铬(Cr) Chromium							
6	4% 乙酸(体积分数), 煮沸 30min, 室温放置 24h 4% acetic acid (v/v), boiled for 30min, leave at room temperature for 24h	mg/kg	未检出 N.D.	0.05	≤ 2.0	符合 Pass	GB 31604.49-2016 第二部分 第一法 The second part The first method
镍(Ni) Nickel							
7	4% 乙酸(体积分数), 煮沸 30min, 室温放置 24h 4% acetic acid (v/v), boiled for 30min, leave at room temperature for 24h	mg/kg	未检出 N.D.	0.05	≤ 0.5	符合 Pass	GB 31604.49-2016 第二部分 第一法 The second part The first method

报告编号: A2210111285101001E
Report No.:

第 5 页共 7 页
Page 5 of 7

备注:

1. DL = 检出限。
- 2.“未检出”表示检测结果小于检出限。
3. 模拟物及迁移试验条件由客户指定。
4. 检测结果为第三次迁移试验的测定结果。
5. 样品实际使用过程中的面积体积比 S/V 未知, 按照标准要求 $6\text{dm}^2/\text{kg}$ (L) 进行迁移试验和结果换算。

Note(s):


1. DL = Detection Limit.
2. N.D. = Not Detected (<DL).
3. Test condition & simulant were specified by client.
4. The test result(s) is (are) the result(s) of the third migration test.
5. The surface to volume ratio (S/V) in actual use is unknown, the migration test was carried out and the test result(s) was (were) converted according to $6\text{ dm}^2/\text{kg}$ (L) regulated in the standard.

报告编号: A2210111285101001E
Report No.:

第 6 页共 7 页
Page 6 of 7

样品图片

Photo(s) of the sample(s)



报告编号: A2210111285101001E
Report No.:

第 7 页共 7 页
Page 7 of 7

*** 报告结束 ***

*** End of report ***

注意:

Attention:

1. 报告无批准人签字、检验检测专用章及报告骑缝章, 或经涂改, 以及复印报告未加盖红色检验检测专用章均视作无效;

This report is considered invalidated in one or more of the following conditions: no approval signature; no testing seal of CTI; no cross-page seal; altered; a copy without the red testing seal of CTI.

2. 未经本公司批准, 不得部分复制本报告;

Without written approval of CTI, this report shall not be reproduced partly.

3. 样品信息由客户提供, 本报告检测结果仅对受检样品负责;

The sample Information is provided by the customer, and the results shown in this test report refer only to the sample(s) tested.

4. 不得擅自使用检测结果进行不当宣传;

Unauthorized use of the test results for improper publicity is impermissible.

5. 如果对检测结果有异议, 请于收到报告之日起 7 个工作日内提出, 逾期不予受理。

Objection to the test results should be raised within 7 working days from the date of receiving the report, otherwise it will not be accepted.

6. 扫描报告首页二维码, 即可查询报告真伪, 如有疑问, 请联系邮箱:
fdd.checkreport@cti-cert.com

Scan the QR code on the first page of the report to verify the authenticity of the report. For any question, please contact the following email: fdd.checkreport@cti-cert.com.